

TECHNICAL DATA SHEET

Epsilon Advanced Conductor 600 - 71

High Temperature Low Sag Conductors

EPSILON
CABLE

International size

ROME


ASTM Size

ARLINGTON



Governing Units: Metric to US Customary (Unit conversion)

STRANDING CONFIGURATION



	Metric			US Customary	
No. & Diameter of composite core	1 x 9.53	mm		1 x 0.375	in.
Aluminum layers construction / Height	36 TW x	3.39	mm	0.133	in.
1st layer composition and Øeq	8 x	4.57	mm	0.180	in.
2nd layer composition and Øeq	12 x	4.60	mm	0.181	in.
3rd layer composition and Øeq	16 x	4.59	mm	0.181	in.
Lay Direction of outer layer	Right Hand (Z)				

CONDUCTOR PROPERTIES


Cross Sectional Area - Annealed Aluminum (1350-O at 63%IACS)	595.3	mm ²	1174.8	kcmil
Cross Sectional Area - Composite Core	71.3	mm ²	0.1106	in. ²
Total Area of Conductor Cross Section	666.6	mm ²	1.0332	in. ²
Nominal equivalent Aluminum Area (1350-H19 at 61%IACS)	614.8	mm ²	1213.3	kcmil
Overall Diameter of Conductor	29.87	mm	1.176	in.
Mass per unit length - Annealed Aluminum	1,647.0	kg/km	1,106.7	lb/kft
Mass per unit length - Core	132.0	kg/km	88.7	lb/kft
Mass per unit length - Conductor	1,779.0	kg/km	1,195.4	lb/kft
Ultimate Tensile Strength of Conductor	195.8	kN	44.0	kips
Core Rated Tensile Strength	160.1	kN	36.0	kips
Coefficient of Linear Expansion Above Thermal Kneepoint	1.3	10 ⁻⁶ K ⁻¹	0.722	10 ⁻⁶ F ⁻¹
Coefficient of Linear Expansion Below Thermal Kneepoint	18.41	10 ⁻⁶ K ⁻¹	10.23	10 ⁻⁶ F ⁻¹
Final Modulus of Elasticity Above Thermal Kneepoint	123	GPa	17.84	Msi
Final Modulus of Elasticity Below Thermal Kneepoint	62	GPa	9.03	Msi

THERMAL SPECIFICATIONS

Maximum Continuous Operating Temperature ⁽²⁾ (surface temperature)	180	°C	356	°F
Maximum Emergency Temperature / 8760 Hours ⁽²⁾ (surface temperature)	200	°C	392	°F
Thermal Heat Capacity for Annealed Aluminum Layers	1,572.9	W-s/m-°C	266.2	W-s/ft-°F
Thermal Heat Capacity for Composite Core	105.6	W-s/m-°C	17.9	W-s/ft-°F

ELECTRICAL SPECIFICATIONS

Maximum DC Electrical Resistance at 20°C / 68°F (1370-O at 63%IACS)	0.0471	ohm/km	0.0758	ohm/mile
Temperature Coefficient of Resistance	4.07	10 ⁻³ K ⁻¹	2.109	10 ⁻³ F ⁻¹
AC Nominal Resistance at 25°C / 77°F (surface temperature)	0.0504	ohm/km	0.0812	ohm/mile
AC Nominal Resistance at 75°C / 167°F (surface temperature)	0.0596	ohm/km	0.0960	ohm/mile
AC Nominal Resistance at 180°C / 356°F (surface temperature)	0.0793	ohm/km	0.1276	ohm/mile
AC Nominal Resistance at 200°C / 392°F (surface temperature)	0.0830	ohm/km	0.1336	ohm/mile
AC Current Rating at 180°C / 356°F (surface temperature) ⁽¹⁾	1,989 A			
AC Current Rating at 200°C / 392°F (surface temperature) ⁽¹⁾	2,104 A			



Geometric Mean Radius (GMR)

12.11 mm 0.0397 ft.

Inductive Reactance Ø0.3m (Ø0.98ft) radius

0.203 Ω.km-1 0.3267 ohm/mile

Capacitive Reactance Ø0.3m (Ø0.98ft) radius

0.173 MΩ.km 0.1075 Mohm-mile

(1) Ampacity calculations based on IEEE Standard 738-2012, according to the following data:

25 °C / 77 °F ambient temperature, 0.61 m/s (2 ft/s) wind velocity with an angle of 90 °,
 1000 W/m² (92.9 W/ft²) solar radiation, 0.5 solar absorption coefficient,
 0.6 emissivity coefficient, Resistance AC at 60 Hz current frequency.

(2) Temperatures defined according to ASTM B987-20.

Reference standards for core properties: ASTM B987-20.

Reference standards for electrical specifications: IEC 62219.

Reference standards for stranding parameters: ASTM B857-14/IEC 62219.

Rated specifications may slightly change depending on conductor manufacturer.

Revision 01

Ref. Document ST21-00048

Date 12-Sep-2023

This document is the property of EPSILON COMPOSITE

contact@epsilon-cable.com
www.epsilon-cable.com