TECHNICAL DATA SHEET

ECRC® 320 - 40


Epsilon Advanced Conductors

EPSILON CABLE

International size	**LISBON**
ASTM Size	**HAWK**
Technical designation	ECRC® 320-AL0/40-S1




Governing Units: Metric to US Customary (Unit conversion)

STRANDING CONFIGURATION		Metric		US Customary	
	*No. & Diameter of composite core*		1 x 7.11 mm	1 x 0.280	in.
	Aluminum layers construction / Height	16 TW x	3.67 mm	0.144	in.
	1st layer composition and Øeq	6 x	5.03 mm	0.198	in.
	2nd layer composition and Øeq	10 x	5.02 mm	0.198	in.
	Lay Direction of outer layer	Right Hand (Z)			

CONDUCTOR PROPERTIES				
Cross Sectional Area - Annealed Aluminum (1350-O at 63%IACS)	316.7	mm²	624.9	kcmil
Cross Sectional Area - Composite Core	39.7	mm²	0.0615	in.²
Total Area of Conductor Cross Section	356.4	mm²	0.5523	in.²
Nominal equivalent Aluminum Area (1350-H19 at 61%IACS)	327.0	mm²	645.4	kcmil
Overall Diameter of Conductor	21.79	mm	0.858	in.
Mass per unit length - Annealed Aluminum	876.0	kg/km	588.6	lb/kft
Mass per unit length - Core	73.5	kg/km	49.4	lb/kft
Mass per unit length - Conductor	949.5	kg/km	638.0	lb/kft
Ultimate Tensile Strength of Conductor	108.1	kN	24.3	kips
Core Rated Tensile Strength	89.1	kN	20.0	kips
Coefficient of Linear Expansion Above Thermal Kneepoint	1.3	10^{-6} K^{-1}	0.722	10^{-6} F^{-1}
Coefficient of Linear Expansion Below Thermal Kneepoint	18.25	10^{-6} K^{-1}	10.13	10^{-6} F^{-1}
Final Modulus of Elasticity Above Thermal Kneepoint	123	GPa	17.84	Msi
Final Modulus of Elasticity Below Thermal Kneepoint	63	GPa	9.08	Msi

THERMAL SPECIFICATIONS				
Maximum Continuous Operating Temperature[2] (surface temperature)	180	°C	356	°F
Maximum Emergency Temperature / 8760 Hours[2] (surface temperature)	200	°C	392	°F
Thermal Heat Capacity for Annealed Aluminum Layers	836.6	W-s/m-°C	141.6	W-s/ft-°F
Thermal Heat Capacity for Composite Core	58.8	W-s/m-°C	9.9	W-s/ft-°F

ELECTRICAL SPECIFICATIONS				
Maximum DC Electrical Resistance at 20°C / 68°F *(1370-O at 63%IACS)*	0.0884	ohm/km	0.1423	ohm/mile
Temperature Coefficient of Resistance	4.03	10^{-3} K^{-1}	2.089	10^{-3} F^{-1}
AC Nominal Resistance at 25°C / 77°F (surface temperature)	0.0915	ohm/km	0.1472	ohm/mile
AC Nominal Resistance at 75°C / 167°F (surface temperature)	0.1091	ohm/km	0.1756	ohm/mile
AC Nominal Resistance at 180°C / 356°F (surface temperature)	0.1462	ohm/km	0.2353	ohm/mile
AC Nominal Resistance at 200°C / 392°F (surface temperature)	0.1533	ohm/km	0.2467	ohm/mile
AC Current Rating at 180°C / 356°F (surface temperature) [1]	1,321 A			
AC Current Rating at 200°C / 392°F (surface temperature) [1]	1,393 A			



Geometric Mean Radius (GMR)				
	8.85	mm	0.0290	ft.
Inductive Reactance Ø0.3m (Ø0.98ft) radius				
	0.222	Ω.km-1	0.3573	ohm/mile
Capacitive Reactance Ø0.3m (Ø0.98ft) radius				
	0.191	MΩ.km	0.1187	Mohm-mile

(1) Ampacity calculations based on IEEE Standard 738-2012, according to the following data:

25 °C / 77 °F ambient temperature, 0.61 m/s (2 ft/s) wind velocity with an angle of 90 °,

1000 W/m² (92.9 W/ft²) solar radiation, 0.5 solar absorption coefficient,

0.6 emissivity coefficient, Resistance AC at 60 Hz current frequency.

(2) Temperatures defined according to ASTM B987-20.

Reference standards for core properties: ASTM B987-20.

Reference standards for electrical specifications: IEC 62219.

Reference standards for stranding parameters: ASTM B857-14/IEC 62219.

Rated specifications may slightly change depending on conductor manufacturer.

Revision 02

Ref. Document ST21-00020

Date 12-Sep-2023

This document is the property of EPSILON COMPOSITE

contact@epsilon-cable.com

www.epsilon-cable.com