TECHNICAL DATA SHEET

ECRC® 600 - 71


Epsilon Advanced Conductors

EPSILON CABLE

International size	**ROME**
ASTM Size	**ARLINGTON**
Technical designation	ECRC® 600-AL0/71-S1




Governing Units: Metric to US Customary (Unit conversion)

STRANDING CONFIGURATION		Metric		US Customary	
	*No. & Diameter of composite core*	1 x 9.53	mm	1 x 0.375	in.
	Aluminum layers construction / Height	36 TW x 3.39	mm	0.133	in.
	1st layer composition and Øeq	8 x 4.57	mm	0.180	in.
	2nd layer composition and Øeq	12 x 4.60	mm	0.181	in.
	3st layer composition and Øeq	16 x 4.59	mm	0.181	in.
	Lay Direction of outer layer	Right Hand (Z)			

CONDUCTOR PROPERTIES				
Cross Sectional Area - Annealed Aluminum (1350-O at 63%IACS)	595.3	mm²	1174.8	kcmil
Cross Sectional Area - Composite Core	71.3	mm²	0.1106	in.²
Total Area of Conductor Cross Section	666.6	mm²	1.0332	in.²
Nominal equivalent Aluminum Area (1350-H19 at 61%IACS)	614.8	mm²	1213.3	kcmil
Overall Diameter of Conductor	29.87	mm	1.176	in.
Mass per unit length - Annealed Aluminum	1,647.0	kg/km	1,106.7	lb/kft
Mass per unit length - Core	132.0	kg/km	88.7	lb/kft
Mass per unit length - Conductor	1,779.0	kg/km	1,195.4	lb/kft
Ultimate Tensile Strength of Conductor	195.8	kN	44.0	kips
Core Rated Tensile Strength	160.1	kN	36.0	kips
Coefficient of Linear Expansion Above Thermal Kneepoint	1.3	10^{-6} K^{-1}	0.722	10^{-6} F^{-1}
Coefficient of Linear Expansion Below Thermal Kneepoint	18.41	10^{-6} K^{-1}	10.23	10^{-6} F^{-1}
Final Modulus of Elasticity Above Thermal Kneepoint	123	GPa	17.84	Msi
Final Modulus of Elasticity Below Thermal Kneepoint	62	GPa	9.03	Msi

THERMAL SPECIFICATIONS				
Maximum Continuous Operating Temperature[2] (surface temperature)	180	°C	356	°F
Maximum Emergency Temperature / 8760 Hours[2] (surface temperature)	200	°C	392	°F
Thermal Heat Capacity for Annealed Aluminum Layers	1,572.9	W-s/m-°C	266.2	W-s/ft-°F
Thermal Heat Capacity for Composite Core	105.6	W-s/m-°C	17.9	W-s/ft-°F

ELECTRICAL SPECIFICATIONS				
Maximum DC Electrical Resistance at 20°C / 68°F *(1370-O at 63%IACS)*	0.0471	ohm/km	0.0758	ohm/mile
Temperature Coefficient of Resistance	4.03	10^{-3} K^{-1}	2.089	10^{-3} F^{-1}
AC Nominal Resistance at 25°C / 77°F (surface temperature)	0.0504	ohm/km	0.0811	ohm/mile
AC Nominal Resistance at 75°C / 167°F (surface temperature)	0.0595	ohm/km	0.0958	ohm/mile
AC Nominal Resistance at 180°C / 356°F (surface temperature)	0.0790	ohm/km	0.1271	ohm/mile
AC Nominal Resistance at 200°C / 392°F (surface temperature)	0.0827	ohm/km	0.1331	ohm/mile
AC Current Rating at 180°C / 356°F (surface temperature) [1]	1,993 A			
AC Current Rating at 200°C / 392°F (surface temperature) [1]	2,108 A			



Geometric Mean Radius (GMR)			
12.11	mm	0.0397	ft.
Inductive Reactance Ø0.3m (Ø0.98ft) radius			
0.203	Ω.km-1	0.3267	ohm/mile
Capacitive Reactance Ø0.3m (Ø0.98ft) radius			
0.173	MΩ.km	0.1075	Mohm-mile

(1) Ampacity calculations based on IEEE Standard 738-2012, according to the following data:

25 °C / 77 °F ambient temperature, 0.61 m/s (2 ft/s) wind velocity with an angle of 90 °,

1000 W/m² (92.9 W/ft²) solar radiation, 0.5 solar absorption coefficient,

0.6 emissivity coefficient, Resistance AC at 60 Hz current frequency.

(2) Temperatures defined according to ASTM B987-20.

Reference standards for core properties: ASTM B987-20.

Reference standards for electrical specifications: IEC 62219.

Reference standards for stranding parameters: ASTM B857-14/IEC 62219.

Rated specifications may slightly change depending on conductor manufacturer.

Revision 02

Ref. Document ST21-00048

Date 12-Sep-2023

This document is the property of EPSILON COMPOSITE

contact@epsilon-cable.com

www.epsilon-cable.com