TECHNICAL DATA SHEET	HVCRC® 190 - 28 Epsilon Advanced Conductors	EPSILON CABLE

International size	**ROVINJ**
ASTM Size	-
Technical designation	ECRC® 190-AL0/28-L1



Governing Units: Metric

STRANDING CONFIGURATION



No. & Diameter of HVCRC core		1 x 5.97	mm
Aluminium Layers Construction / height	16 TW x	2.78	mm
1st layer composition and Øeq	6 x	3.92	mm
2nd layer composition and Øeq	10 x	3.86	mm
Lay Direction of outer layer		Right Hand (Z)	

CONDUCTOR PROPERTIES


Cross Sectional Area - Annealed Aluminium	189.1	mm²
Cross Sectional Area - HVCRC Core	28.0	mm²
Total Area of Conductor Cross Section	217.1	mm²
Nominal equivalent Aluminium Area (1350-H19 at 61%IACS)	195.3	mm²
Overall Diameter of Conductor	17.09	mm
Mass per unit length - Annealed Aluminium	523.1	kg/km
Mass per unit length - Core	52.6	kg/km
Mass per unit length - Conductor	575.7	kg/km
Ultimate Tensile Strength of Conductor	71.2	kN
Core Rated Tensile Strength	59.8	kN
Coefficient of Linear Expansion **Above** Thermal Kneepoint	1.6	10^{-6} K^{-1}
Coefficient of Linear Expansion **Below** Thermal Kneepoint	18.04	10^{-6} K^{-1}
Final Modulus of Elasticity **Above** Thermal Kneepoint	112	GPa
Final Modulus of Elasticity **Below** Thermal Kneepoint	62	GPa

THERMAL SPECIFICATIONS

Maximum Continuous Operating Temperature[2] (surface temperature)	180	°C
Maximum Emergency Temperature / 8760 Hours[2] (surface temperature)	200	°C
Thermal Heat Capacity for Annealed Aluminium Layers	499.6	W.s/m.°C
Thermal Heat Capacity for Composite Core	42.1	W.s/m.°C

ELECTRICAL SPECIFICATIONS

Maximum DC Electrical Resistance at 20°C *(1370-O at 63%IACS)*	0.1481	Ω.km^{-1}
Temperature Coefficient of Resistance	4.03	10^{-3} K^{-1}
AC Nominal Resistance at 25°C (surface temperature)	0.1516	Ω.km^{-1}
AC Nominal Resistance at 75°C (surface temperature)	0.1814	Ω.km^{-1}
AC Nominal Resistance at 160°C (surface temperature)	0.2320	Ω.km^{-1}
AC Nominal Resistance at 180°C (surface temperature)	0.2439	Ω.km^{-1}
AC Nominal Resistance at 200°C (surface temperature)	0.2559	Ω.km^{-1}
AC Current Rating at 160°C (surface temperature) [1]	892	A
AC Current Rating at 180°C (surface temperature) [1]	946	A
AC Current Rating at 200°C (surface temperature) [1]	997	A



Geometric Mean Radius (GMR)	
6.98	mm
Inductive Reactance Ø0.3m radius	
0.237	Ω.km^{-1}
Capacitive Reactance Ø0.3m radius	
0.205	MΩ.km

(1) Ampacity calculations based on IEEE Standard 738-2012, according to the following data:

25 °C ambient temperature, *0.61 m/s wind velocity with an angle of 90 °,*

1000 W/m² solar radiation, *0.5 solar absorption coefficient,*

0.6 emissivity coefficient, *Resistance AC at 50 Hz current frequency.*

(2) Temperatures defined according to ASTM B987-20.

Reference standards for core properties: ASTM B987-20.

Reference standards for electrical specifications: IEC 62219.

Reference standards for stranding parameters: ASTM B857-14/IEC 62219.

Depending on conductor manufacturer rated specifications may slightly change.

Revision	*05*
Ref. Document	*ST21-00143*
Date	*6-Jun-2025*

This document is the property of EPSILON COMPOSITE

contact@epsilon-cable.com

www.epsilon-cable.com