
TECHNICAL DATA SHEET	Ultra Low Sag (ULS)	**ECRC® ULS 950 - 75** Epsilon Advanced Conductors	EPSILON CABLE


International size	**ANTWERP**
ASTM Size	**DALLAS**
Technical designation	ECRC® 950-AL0/75-X1



Governing Units: Metric to US Customary (Unit conversion)

STRANDING CONFIGURATION		Metric		US Customary	
	*No. & Diameter of the core*		1 x 9.78 mm	1 x 0.385	in.
	Aluminium layers construction / Height	42 TW x	4.52 mm	0.178	in.
	1st layer composition and Øeq	9 x	5.25 mm	0.207	in.
	2nd layer composition and Øeq	14 x	5.35 mm	0.211	in.
	3st layer composition and Øeq	19 x	5.39 mm	0.212	in.
	Lay Direction of outer layer	Right Hand (Z)			

CONDUCTOR PROPERTIES				
Cross Sectional Area - Annealed Aluminum (1350-O at 63%IACS)	943.6	mm²	1862.2	kcmil
Cross Sectional Area - Composite Core	75.1	mm²	0.1164	in.²
Total Area of Conductor Cross Section	1,018.7	mm²	1.5790	in.²
Nominal equivalent Aluminum Area (1350-H19 at 61%IACS)	974.5	mm²	1923.2	kcmil
Overall Diameter of Conductor	36.9	mm	1.453	in.
Mass per unit length - Annealed Aluminum	2,612.0	kg/km	1,755.2	lb/kft
Mass per unit length - Core	138.2	kg/km	92.9	lb/kft
Mass per unit length - Conductor	2,750.2	kg/km	1,848.1	lb/kft
Ultimate Tensile Strength of Conductor	250.9	kN	56.4	kips
Core Rated Tensile Strength	194.3	kN	43.7	kips
Coefficient of Linear Expansion Above Thermal Kneepoint	0.75	10^{-6} K^{-1}	0.417	10^{-6} F^{-1}
Coefficient of Linear Expansion Below Thermal Kneepoint	19.12	10^{-6} K^{-1}	10.62	10^{-6} F^{-1}
Final Modulus of Elasticity Above Thermal Kneepoint	146	GPa	21.18	Msi
Final Modulus of Elasticity Below Thermal Kneepoint	62	GPa	8.95	Msi
THERMAL SPECIFICATIONS				
Maximum Continuous Operating Temperature[2] (surface temperature)	180	°C	356	°F
Maximum Emergency Temperature / 8760 Hours[2] (surface temperature)	200	°C	392	°F
Thermal Heat Capacity for Annealed Aluminum Layers	2,494.5	W-s/m-°C	422.2	W-s/ft-°F
Thermal Heat Capacity for Composite Core	110.6	W-s/m-°C	18.7	W-s/ft-°F
ELECTRICAL SPECIFICATIONS				
Maximum DC Electrical Resistance at 20°C / 68°F *(1370-O at 63%IACS)*	0.0297	ohm/km	0.0478	ohm/mile
Temperature Coefficient of Resistance	4.03	10^{-3} K^{-1}	2.089	10^{-3} F^{-1}
AC Nominal Resistance at 25°C / 77°F (surface temperature)	0.0338	ohm/km	0.0545	ohm/mile
AC Nominal Resistance at 75°C / 167°F (surface temperature)	0.0393	ohm/km	0.0633	ohm/mile
AC Nominal Resistance at 180°C / 356°F (surface temperature)	0.0512	ohm/km	0.0824	ohm/mile
AC Nominal Resistance at 200°C / 392°F (surface temperature)	0.0535	ohm/km	0.0861	ohm/mile
AC Current Rating at 180°C / 356°F (surface temperature) [1]	2,659 A			
AC Current Rating at 200°C / 392°F (surface temperature) [1]	2,821 A			



Geometric Mean Radius (GMR)			
14.76	mm	0.0484	ft.
Inductive Reactance Ø0.3m (Ø0.98ft) radius			
0.19	Ω.km-1	0.3058	ohm/mile
Capacitive Reactance Ø0.3m (Ø0.98ft) radius			
0.161	MΩ.km	0.1000	Mohm-mile

(1) Ampacity calculations based on IEEE Standard 738-2012, according to the following data:

25 °C / 77 °F ambient temperature, 0.61 m/s (2 ft/s) wind velocity with an angle of 90 °,

1000 W/m² (92.9 W/ft²) solar radiation, 0.5 solar absorption coefficient,

0.6 emissivity coefficient, Resistance AC at 60 Hz current frequency.

(2) Temperatures defined according to ASTM B987.

Reference standards for core properties: ASTM B987.

Reference standards for electrical specifications: IEC 62219.

Reference standards for stranding parameters: ASTM B857-14/IEC 62219.

Depending on conductor manufacturer rated specifications may slightly change.

Revision 00

Ref. Document ST25-00073

Date 14-Aug-2025

This document is the property of EPSILON COMPOSITE

contact@epsilon-cable.com

www.epsilon-cable.com