| TECHNICAL DATA SHEET | Lite | HVCRC® Lite (AL1) 430 - 52<br>Epsilon Advanced Conductors | EPSILON CABLE |
|---|---|---|---|

| | |
|---|---|
| International size | **BRUSSELS** |
| ASTM Size | **GROSBEAK** |
| Technical designation | ECRC® 430-AL1/52-L0 |



*Governing Units: Metric*

| | | |
|---|---|---|
| **CONDUCTOR PROPERTIES** | | |
| Cross Sectional Area - Aluminium | 421.7 | mm² |
| Cross Sectional Area - HVCRC Core | 51.9 | mm² |
| Total Area of Conductor Cross Section | 473.6 | mm² |
| Overall Diameter of Conductor | 25.13 | mm |
| No. & Diameter of the core | 1 x 8.13 | mm |
| Mass per unit length - Annealed Aluminium | 1,166.0 | kg/km |
| Mass per unit length - Core | 97.6 | kg/km |
| Mass per unit length - Conductor | 1,263.6 | kg/km |
| Ultimate Tensile Strength of Conductor | 125.6 | kN |
| Core Rated Tensile Strength | 58.1 | kN |
| Coefficient of Linear Expansion **Above** Thermal Kneepoint | 1.6 | $10^{-6}$ $K^{-1}$ |
| Coefficient of Linear Expansion **Below** Thermal Kneepoint | 18.71 | $10^{-6}$ $K^{-1}$ |
| Final Modulus of Elasticity **Above** Thermal Kneepoint | 112 | GPa |
| Final Modulus of Elasticity **Below** Thermal Kneepoint | 61 | GPa |
| **THERMAL SPECIFICATIONS** | | |
| Maximum Continuous Operating Temperature (surface temperature) | 90 | °C |
| Thermal Heat Capacity for Annealed Aluminium Layers | 1,113.5 | W.s/m.°C |
| Thermal Heat Capacity for Composite Core | 78.1 | W.s/m.°C |
| **ELECTRICAL SPECIFICATIONS** | | |
| Maximum DC Electrical Resistance at 20°C | 0.0687 | $\Omega.km^{-1}$ |
| Temperature Coefficient of Resistance | 4.03 | $10^{-3}$ $K^{-1}$ |
| AC Nominal Resistance at 25°C (surface temperature) | 0.0713 | $\Omega.km^{-1}$ |
| AC Nominal Resistance at 75°C (surface temperature) | 0.0849 | $\Omega.km^{-1}$ |
| AC Nominal Resistance at 90°C (surface temperature) | 0.0890 | $\Omega.km^{-1}$ |
| AC Current Rating at 90°C (surface temperature)[1] | 1,043 | A |
| Geometric Mean Radius (GMR) | 10.20 | mm |

*(1) Ampacity calculations based on IEEE Standard 738-2012, according to the following data:*

*25 °C ambient temperature,* — *0.61 m/s wind velocity with an angle of 90 °,*

*1000 W/m² solar radiation,* — *0.5 solar absorption coefficient,*

*0.6 emissivity coefficient,* — *Resistance AC at 50 Hz current frequency.*

*Conductor continuous operating temperature can be changed in accordance with country specification for hard aluminium.*

*Core properties tested as per methods of ASTM B987/IEC 62818-1*

*Reference standards for electrical specifications: IEC 62219.*

*Reference standards for stranding parameters: ASTM B779/IEC 62219.*

*Depending on conductor manufacturer rated specifications may slightly change.*

| | |
|---|---|
| *Revision* | *00* |
| *Ref. Document* | *ST26-00071* |
| *Date* | *6-Mar-2026* |

*This document is the property of EPSILON COMPOSITE*

contact@epsilon-cable.com

www.epsilon-cable.com