TECHNICAL DATA SHEET	Lite	HVCRC® Lite (AL1) 950 - 75 Epsilon Advanced Conductors	EPSILON CABLE

International size	**ANTWERP**
ASTM Size	**DALLAS**
Technical designation	ECRC® 950-AL1/75-L0



Governing Units: Metric

CONDUCTOR PROPERTIES		
Cross Sectional Area - Aluminium	943.6	mm²
Cross Sectional Area - HVCRC Core	75.1	mm²
Total Area of Conductor Cross Section	1,018.7	mm²
Overall Diameter of Conductor	36.9	mm
No. & Diameter of the core	1 x 9.78	mm
Mass per unit length - Annealed Aluminium	2,612.0	kg/km
Mass per unit length - Core	141.2	kg/km
Mass per unit length - Conductor	2,753.2	kg/km
Ultimate Tensile Strength of Conductor	235.1	kN
Core Rated Tensile Strength	84.1	kN
Coefficient of Linear Expansion **Above** Thermal Kneepoint	1.6	10^{-6} K^{-1}
Coefficient of Linear Expansion **Below** Thermal Kneepoint	20.01	10^{-6} K^{-1}
Final Modulus of Elasticity **Above** Thermal Kneepoint	112	GPa
Final Modulus of Elasticity **Below** Thermal Kneepoint	59	GPa
THERMAL SPECIFICATIONS		
Maximum Continuous Operating Temperature (surface temperature)	90	°C
Thermal Heat Capacity for Annealed Aluminium Layers	2,494.5	W.s/m.°C
Thermal Heat Capacity for Composite Core	113.0	W.s/m.°C
ELECTRICAL SPECIFICATIONS		
Maximum DC Electrical Resistance at 20°C	0.0308	$\Omega.km^{-1}$
Temperature Coefficient of Resistance	4.03	10^{-3} K^{-1}
AC Nominal Resistance at 25°C (surface temperature)	0.0338	$\Omega.km^{-1}$
AC Nominal Resistance at 75°C (surface temperature)	0.0397	$\Omega.km^{-1}$
AC Nominal Resistance at 90°C (surface temperature)	0.0414	$\Omega.km^{-1}$
AC Current Rating at 90°C (surface temperature)[1]	1,710	A
Geometric Mean Radius (GMR)	14.76	mm

(1) Ampacity calculations based on IEEE Standard 738-2012, according to the following data:

25 °C ambient temperature, — *0.61 m/s wind velocity with an angle of 90 °,*

1000 W/m² solar radiation, — *0.5 solar absorption coefficient,*

0.6 emissivity coefficient, — *Resistance AC at 50 Hz current frequency.*

Conductor continuous operating temperature can be changed in accordance with country specification for hard aluminium.

Core properties tested as per methods of ASTM B987/IEC 62818-1

Reference standards for electrical specifications: IEC 62219.

Reference standards for stranding parameters: ASTM B779/IEC 62219.

Depending on conductor manufacturer rated specifications may slightly change.

Revision	*00*
Ref. Document	*ST26-00086*
Date	*6-Mar-2026*

This document is the property of EPSILON COMPOSITE

contact@epsilon-cable.com

www.epsilon-cable.com